



Technical Data Sheet

Revision 00 of 20.10.2012

K2 MDF

DESCRIPTION:

Filler compound with polyester resins and special mineral charges with an addition of wood floor.

It is particularly recommended for restorations of ancient furniture (remaking of wood particulars)

and all what foresees the employment of the wood (houses, fixtures, boats, etc...)

PHYSICAL – CHEMICAL CHARACTERISTICS:

Specific weight:	1200 g/l
Colour:	pursuant on labelling
Shelf-life:	12 month in a dry and fresh place, far from heathing points
Flexibility:	good
Shrinkage:	none
Resistance to water and thinner:	excellent
Dry residue:	78% in weight

METHOD OF USAGE:

Clean the surface carefully; brann using an anti-siliconic thinner. Add the hardener to the filler with

reference to the room temperature:

TEMPERATURE	HARDENER WEIGHT
Less than 10°C	3 – 3,5 %
10-20°C	2 – 2,5 %
More than 20°C	1 - 1,5 %

Mix the two components well

POT-LIFE: 4-6 min. at 20°C



BORMA WACHS[®]

Wood Professional Cosmetics

PACKAGE:

The product comes in 750 mL cans and 820 mL cartridges.

STORAGE:

Store in a cool, well ventilated place, keep the container closed when not in use. Keep away from heat, flames, sparks and other sources of ignition.

WARNING:

Our data sheets are prepared on the basis of average performance of our tests. However, our technical advices are given in good faith but without any warranty. In fact different supports, conditions of application, industrial plants, dilutions are determinant for the final result, and are often beyond our control. The user must try the product to see if it is suitable for his needs. We will ensure the continuity of the chemical-physical characteristics.